

<i>Description</i>	<i>Product ID</i>	<i>Melt Point</i>	<i>Plasticizers</i>	<i>Home Wash</i>	<i>Industrial Wash</i>	<i>Dry Clean</i>	<i>Polyester</i>	<i>Polycotton</i>	<i>Nylon</i>	<i>Lycra</i>	<i>ABS</i>	<i>Polycarbonate</i>	<i>Polypropylene</i>	<i>PVC</i>	<i>Polyurethane</i>	<i>Wood</i>	<i>Leather</i>	<i>Rubber / Neop.</i>	<i>Fiberglass</i>	<i>Aluminum</i>	<i>Copper</i>	<i>Steel</i>
POLYESTER	PAF-110	265° - 285° F 130° - 140° C	◆	◆		◆	◆	◆				◆		◆	◆	◆	◆		◆	◆	◆	◆
	PAF-129	140° - 165° F 60° - 75° C	◆	◆			◆	◆	◆	◆	◆			◆	◆	◆	◆	◆	◆	◆	◆	◆
	PAF-130	230° - 250° F 110° - 120° C	◆	◆		◆	◆							◆	◆	◆	◆		◆	◆	◆	◆
	PAF-160	300° - 320° F 150° - 160° C	◆	◆	◆	◆	◆	◆							◆	◆					◆	◆
URETHANE	UAF-415	275° - 295° F 135° - 145° C	◆	◆	◆	◆	◆	◆		◆	◆			◆	◆	◆	◆	◆	◆			
	UAF-438	175° - 195° F 80° - 90° C	◆	◆		◆	◆	◆	◆	◆	◆			◆	◆	◆	◆	◆	◆	◆	◆	◆
	UAF-445	300° - 330° F 150° - 165° C	◆	◆	◆	◆	◆	◆		◆	◆			◆	◆	◆	◆		◆	◆	◆	◆
	UAF-472	205° - 215° F 95° - 105° C	◆	◆		◆		◆	◆	◆	◆			◆	◆	◆	◆	◆	◆	◆	◆	◆
	UAF-487	175° - 195° F 80° - 90° C	◆	◆		◆	◆	◆	◆	◆	◆			◆	◆	◆	◆	◆	◆	◆	◆	◆
NYLON	NAF-605	210° - 230° F 100° - 110° C	◆	◆			◆	◆	◆	◆				◆	◆	◆	◆	◆	◆			
	NAF-610	260° - 280° F 130° - 140° C		◆		◆	◆	◆							◆	◆						◆
ETHYLENE	EAF-220	160° - 170° F 70° - 77° C						◆		◆		◆	◆			◆	◆	◆	◆	◆	◆	◆
	EAF-235	165° - 185° F 75° - 85° C						◆	◆			◆	◆			◆	◆	◆	◆	◆	◆	◆